저작자표시-비영리-변경금지 2.0 대한민국

이용자는 아래의 조건을 따르는 경우에 한하여 자유롭게

- 이 저작물을 복제, 배포, 전송, 전시, 공연 및 방송할 수 있습니다.

다음과 같은 조건을 따라야 합니다:

저작자표시. 귀하는 원저작자를 표시하여야 합니다.

비영리. 귀하는 이 저작물을 영리 목적으로 이용할 수 없습니다.

변경금지. 귀하는 이 저작물을 개작, 변형 또는 가공할 수 없습니다.

- 귀하는, 이 저작물의 재이용이나 배포의 경우, 이 저작물에 적용된 이용허락조건을 명확하게 나타내어야 합니다.
- 저작권자로부터 별도의 허가를 받으면 이러한 조건들은 적용되지 않습니다.

저작권법에 따른 이용자의 권리는 위의 내용에 의하여 영향을 받지 않습니다.

이것은 [이용허락규약\(Legal Code\)](#)을 이해하기 쉽게 요약한 것입니다.

[Disclaimer](#)

工學碩士學位論文

**Designed synthesis of $\text{SiO}_2/\text{TiO}_2$
core/shell structure as light scattering
material for highly efficient
dye-sensitized solar cells**

실리카/티타니아 코어/셸 구조의 제조와
염료감응태양전지의 빛 산란물질로의 응용

2013年 2月

서울대학교 大學院

化學生物工學部

孫 秀 任

Abstract

Designed synthesis of SiO₂/TiO₂ core/shell structure as light scattering material for highly efficient dye-sensitized solar cells

Suim Son

School of Chemical and Biological Engineering

The Graduate School

Seoul National University

SiO₂/TiO₂ core/shell nanoparticles (STCS-NPs) with diameters of 110, 240, 530 nm were fabricated to investigate the influence of the size and refractive index of light-scattering particles on light-scattering properties. The optical properties of STCS-NPs were evaluated and compared with SiO₂-NPs and TiO₂-NPs. Considering the size effect, the reflectance gets higher with increasing size of NPs.

Also, it was shown that the structure of the STCS-NPs, consisting of a low refractive index core and high refractive index shell, contributed to the high scattering efficiency. Dye-sensitized solar cells (DSSC) containing STCS-NPs exhibited an enhanced power conversion efficiency (PCE) of 20% compared with the pristine DSSC.

Keywords: Dye-sensitized solar cells, light-scattering material, core/shell nanoparticle

Student Number: 2011-22919

Contents

Chapter 1. Introduction	1
1.1 Dye-sensitized solar cells.....	1
1.2 Light-scattering nanostructures.....	4
1.2.1 Light-scattering materials	4
1.2.2 Light-scattering theory.....	5
1.2.3 Core/shell nanoparticles.....	6
1.3 Characteristics of SiO ₂ and TiO ₂	7
1.3.1 SiO ₂	7
1.3.2 TiO ₂	8
1.4 Objective of this study	10
Chapter 2. Experimental.....	12
2.1 Preparation of SiO ₂ , TiO ₂ , STCS NPs	12
2.1.1 SiO ₂ -NPs.....	12
2.1.2 TiO ₂ -NPs.....	13
2.1.3 STCS-NPs.....	14
2.2 Solar cell preparation	15

2.3	Characterization	16
Chapter 3.	Results and discussion.....	17
3.1	Fabrication and microscopic observation of the STCS-NPs.	17
3.2	Optical property analysis	25
3.3	Photovoltaic performance of DSSCs	32
Chapter 4	Conclusion	45
References		47
Abstract		52

List of Figures

Figure 1.	Principle of operation and energy level scheme of the dye-sensitized nanocrystalline solar cell.....	3
Figure 2.	Transmission electron microscopy (TEM) images and field-emission scanning electron microscopy (FE-SEM) images of (a, d) STCS-NPs with diameters of <i>ca.</i> 110 nm, (b, e) STCS-NPs with diameters of <i>ca.</i> 240 nm, (c, f) STCS-NPs with diameters of <i>ca.</i> 530 nm.....	18
Figure 3.	SEM/Energy dispersive X-ray spectroscopy (EDX) spectra of (a) CS110, (b) CS240 and (c) CS530 NPs. The diameter of CS-NPs is 110 nm, 240 nm, 530 nm and shell thickness is identical as 10 nm after weight ratio calculation... ..	20
Figure 4.	STEM-EDX line mapping of (a) CS110, (b) CS240 and (c) CS530 NPs.	22
Figure 5.	X-ray diffraction (XRD) patterns for a) CS110, b) CS240 and c) CS530 NPs... ..	24
Figure 6.	(a) Diffused reflectance spectra (DRS) and (b) UV-Vis absorption spectra of 110 nm, 240 nm, 530 nm STCS-NPs.....	27
Figure 7.	(a) Diffuse reflectance spectra (DRS) and (b) UV-Vis absorption	

	spectra of SiO ₂ -NPs, TiO ₂ -NPs, and STCS-NPs	28
Figure 8.	Schematic illustration for light scattering by (a) TiO ₂ -NP and (b) STCS-NP on the basis of geometric optics..	31
Figure 9.	Schematic configuration of a dye-sensitized solar cell (DSSC) that has SiO ₂ /TiO ₂ core/shell nanoparticles (STCS-NPs) incorporating nanocrystalline TiO ₂ particles in the working electrode.	34
Figure 10.	Cross-section FESEM image of STCS-NPs incorporated with nanocrystalline TiO ₂ paste on the electrode. (Inset: surface SEM image of the film. Black arrows indicate incorporated STCS-NPs.).	35
Figure 11.	Photocurrent density-voltage curve (J-V curve) of a DSSC based on STCS-NPs with various diameters.....	38
Figure 12.	Incident-photon-to-current conversion efficiency (IPCE) spectra of a DSSC based on STCS-NPs with various diameters.....	39
Figure 13.	Photocurrent density-voltage curve (J-V curve) of a DSSC based on SiO ₂ -NPs, TiO ₂ -NPs, and STCS-NPs as scattering materials... ..	42
Figure 14.	Incident-photon-to-current conversion efficiency (IPCE) spectra of a DSSC based on SiO ₂ -NPs, TiO ₂ -NPs, and STCS-NPs as	

scattering materials.....	43
---------------------------	----

List of Tables

Table 1.	SEM/EDX results of the STCS-NPs with diameters of 110 nm, 240 nm and 530 nm..	21
Table 2.	Comparison of short-circuit photocurrent density (J_{sc}), open-circuit voltage (V_{oc}), fill factor (FF), and power conversion efficiency (PCE).....	44

Chapter 1. Introduction

1.1 Dye-sensitized solar cells

Dye-sensitized solar cells (DSSCs), introduced by O'Regan and Grätzel in 1991, have emerged as promising candidates for next-generation solar cells.[1–2] Up until now, the overall power conversion efficiency (PCE) of DSSCs has reached up to 12%.[3]

Figure 1 displays a schematic presentation of the operation principles of the DSSC.[4] The core of a DSSC is the mesoporous oxide layer composed of nanocrystalline particles. Mostly TiO_2 has been used for the material for the oxide layer, but other wide band gap oxides such as ZnO , and Nb_2O_5 have also been investigated. The mesoporous oxide layer is commonly deposited on glass coated with fluorine-doped tin oxide (FTO). The charge transfer dye is attached to the surface of the

nanocrystalline film. Photoexcitation of the dye results in the injection of an electron into the conduction band of the oxide. The dye molecules regain the lost electrons by electron transfer from the electrolyte, usually an organic solvent containing the iodide/triiodide redox system.

[5]

A great deal of effort has been devoted to improving efficiency of DSSCs such as using low-volatility electrolytes, modifying counter-electrode materials, and post-treatment with a TiCl_4 precursor.[6] Especially, various approaches have been developed for light harvesting in the working electrode, including increasing the surface area of the metal oxide,[7, 8] developing new dyes with broad absorption spectra,[9, 10] and introducing light-scattering materials.

Figure. 1 Principle of operation and energy level scheme of the dye-sensitized nanocrystalline solar cell. [4]

1.2 Light-scattering nanostructures

1.2.1. Light-scattering materials

Light-scattering materials (LSMs) were proposed to improve light absorption in the working electrode. The LSMs are effective in enhancing the light-harvesting capability of the working electrode so as to improve DSSC performance.[11] The light-scattering mechanism consists of two components: optical confinement and increasing the absorption path length. Optical confinement occurs when backscattered light from LSMs becomes trapped in the working electrode; On the other hand, forward-scattered light from LSMs increase the path length in the forward direction; Comparing these two components, optical confinement has a greater effect on enhancing PCE than increasing the path length in the forward direction.[12] Based on these optical properties of LSMs, various LSM morphologies have been studied including spheres,[13, 14] nanofibers,[15–17] and hollow particles.[18] Also, LSMs with different refractive indices have been investigated

such as TiO_2 , SiO_2 , or Al_2O_3 . [11]

1.2.2. Light scattering theory

Light scattering theory can be categorized in terms of two theoretical frameworks. One is the Rayleigh scattering theory that is applicable to small, dielectric, spherical particles. The second is theory of Mie scattering that includes most spherical scattering particles without a particular boundary on particle size. In DSSCs, the Rayleigh scattering from nanocrystalline TiO_2 is weak scattering, resulting in most of the incident light to TiO_2 film transmitting through the film. Particularly, Mie scattering happens when the size of the particles is comparable to the wavelength of the incident light. The light harvesting efficiency is enhanced by Mie scattering resulting from the incorporation of large size particles. Ferber *et al.* suggested the use of large TiO_2 particles 240-300 nm in diameter as LSMs incorporating with 20 nm particles. [19] Wang *et al.* mixed 23 nm TiO_2 particles with 110 nm TiO_2 particles and achieved a higher efficiency than the DSSC

made from only 20 nm particles.[20]

1.2.3. Core/shell nanoparticles

Among the LSMs, theoretical studies have been performed to understand the scattering effect of core/shell nanoparticles, due to their wide range of optical manifestations.[31–33] Studies of core/shell structure by several research groups indicated that scattering efficiency depended on the thickness of the shell, the particle size, size distribution, shape, and refractive index. Hsu *et al.* reported that high scattering efficiency could be achieved using an SiO₂/TiO₂ core/shell particle with optimum diameter of 0.8-1.0 μm and shell thickness of 0.2-0.3 μm.[34] These results were based on theoretical calculations as a function of the particle's optical size and the shell thickness. Small *et al.* discussed theoretical models that showed improvement in the scattering efficiency for the core/shell structure when the refractive index of the shell material was significantly different than that of surrounding matrix, compared with the core material.[35] However,

relatively little attention has been paid to the experimental studies and application of the core/shell structure to DSSCs. It is still challenging to synthesize $\text{SiO}_2/\text{TiO}_2$ core/shell structures as LSMs for solar cell applications.

1.3. Characteristics of SiO_2 and TiO_2

1.3.1. SiO_2

Silicon dioxide, also known as silica, is an oxide of silicon with the chemical formula SiO_2 . SiO_2 is commonly found in nature as sand or quartz. SiO_2 is used primarily in the production of glass for windows, drinking glasses, beverage bottles, optical fibers and many other uses.[21]

SiO_2 is precisely controllable to diverse shapes by many synthetic ways, biocompatible, and easy to modify its surface. Due to these

characteristics, SiO_2 has received considerable attention in nanotechnology in these days.

One of the most widely used silica form in nanotechnology is colloidal silica, which is used for filler of composites, support of nanomaterials, template to fabricate nanomaterials, and so on. Recently, mesoporous silica is developed in nanotechnology.[22, 23] It has large surface area and pore volume suitable for high performance catalyst supports, drug delivery, and biosensors.[24, 25] Above these forms, various silica nanostructures have been reported and studied in diverse application fields including scattering materials for DSSCs.[26]

1.3.2. TiO_2

Titanium oxide, also known as titania, is the naturally occurring oxide of titanium, chemical formula TiO_2 . Generally, TiO_2 is found to

be rutile, anatase, and brookite forms in nature. Rutile is the most crystalline form because it is equilibrium phase at all temperatures. The metastable anatase and brookite phases both convert to rutile by heating.[27]

TiO₂ has been widely used as a white pigment which is included in paints because of its high refractive index, oil absorption, and inert chemical properties. Recently, TiO₂ has received considerable attention due to its suitable properties for photocatalyst and solar energy conversion based on dye, polymer, or quantum dot sensitized solar cells.[28–30] In DSSCs, the nanoporous TiO₂ sensitized by a dye plays the essential role of transferring electrons. To develop highly efficient DSSCs, various morphology of TiO₂ nanoparticles which have high surface area and fast electron mobility have been studied. It is still required to fabricate the novel class of TiO₂ nanomaterials as a material for renewable energy conversion, although

various TiO_2 nanoparticles have been prepared from versatile synthetic routes.

1.4. Objective of this study

Herein, we report the size-controllable fabrication of $\text{SiO}_2/\text{TiO}_2$ core/shell nanoparticles (STCS-NPs) using SiO_2 -template sol-gel method. STCS-NPs with 110 nm, 240 nm, 530 nm size were prepared and the scattering properties of the STCS-NPs were investigated by diffuse reflection spectroscopy (DRS). And the optical property of STCS-NP with 240 nm in diameter (ST240-NP) was compared with that of SiO_2 -NPs and TiO_2 -NPs, whose diameters are identical to STCS-NPs. A 240-nm size was selected for the LSMs because scattering particles with 200–300 nm in diameter exhibited the high scattering efficiency when incorporated with nanocrystalline TiO_2

(15–20 nm).[37] Additionally, STCS-NPs were applied to DSSCs as scattering materials, and their photovoltaic properties were evaluated.

Chapter 2. Experimental

2.1 Preparation of SiO₂, TiO₂, and STCS NPs

2.1.1 SiO₂-NPs

Monodisperse SiO₂-NPs 90, 220, 240, 510 nm in diameter were prepared via seed regrowth method.[38] First of all, 0.058 g of arginine was dissolved in 58 g of water with stirring. 3.47 g of tetraethyl orthosilicate (TEOS) was added to the solution and vigorously stirred at 343 K for 24 h to prepare SiO₂ seed 14 nm in size. After 24 h, the obtained SiO₂ seed solution was added to mixed solution of 33.379 g of ethanol, 10.35 g of water, 0.0653 g of arginine with stirring. The solution was stirred at 343 K for several minutes and TEOS was added to the solution for 24 h. The sizes of the SiO₂-NPs were controlled by adjusting the amount of TEOS consumed for the

formation of the seed($M_{\text{TEOS, seed}}$) and TEOS added to the seed dispersion($M_{\text{TEOS, addition}}$). The final product was obtained after washing the solution several times with water and drying in a convection oven at 60 °C.

2.1.2 TiO₂-NPs

TiO₂ nanoparticles were synthesized via sol-gel reaction. First, 110 mL of absolute ethanol was mixed with 1.5 mL water. Then, a solution containing 1 ml of titanium isopropoxide (TTIP) and 9 mL of absolute ethanol was dropwised into the 110 mL of absolute ethanol and 1.5 mL of water with vigorous stirring at 298 K for 24 h. The resulting solution was washed several times with water and dried in a vacuum oven at room temperature. The final product was obtained after calcining the powder at 530 °C for 2 h.

2.1.3 STCS-NPs

The prepared SiO₂-NPs with diameter of 90, 220, 510 nm were used to synthesize STCS-NPs with 10 nm shell thickness. Solution containing 79 mL of ethanol, 3.9 mL of ammonia solution, and 1.4 mL of water was mixed with SiO₂-NPs to obtain SiO₂ colloidal solution. Then, 28 mL of acetonitrile was added to the solution with stirring at 4 °C. Another solution containing 36 mL of ethanol, 12 mL of acetonitrile, 1 mL of TTIP was prepared followed by dropwise addition to the colloidal SiO₂ solution. The mixture was vigorously stirred for 12 h. Subsequently, the resulting white solution was dried in oven at 110 °C. The final product was obtained after calcining dried white powder at 600 °C for 6 h.[39]

2.2 Solar cell preparation

To prepare a paste with scattering material, SiO₂, TiO₂, STCS-NPs were mixed with screen-printable TiO₂ nanoparticle paste respectively (Solaronix, Ti-Nanoxide T/sp). The TiO₂ nanoparticle films containing scattering materials were screen-printed on fluorine-doped tin oxide (FTO) glass precoated with TiCl₄ solution, which was heated at 450 °C for 30 min. The coated films were baked over the same heating profile used previously. For dye adsorption, the resulting TiO₂ films were immersed in anhydrous ethanol containing D719 dye, and kept at room temperature for 24 h. Pt counter electrodes were prepared by dropping 5 mM H₂PtCl₆ solution, followed by heating at 400 °C for 30 min in air. In a sealed cell, iodide-based electrolyte (Idolyte AN-50, Solaronix) was introduced.

2.3 Characterization

The morphology of the scattering particles was investigated by transmission electron microscopy (TEM, JEOL JEM-200CX). X-ray diffraction (XRD) data were obtained using an M18XHF-SRA (Mac Science Co.) with a Cu K α radiation source ($\lambda = 1.5406 \text{ \AA}$) at 40 kV and 300 mA (12 kW). Lamda 35 (Perkin-Elmer) provided the spectra of UV-vis diffuse reflectance spectroscopy (DRS). The cross-section TiO₂ films on the FTO were examined by field-emission scanning electron microscopy (FE-SEM, JEOL 6700). The photocurrent-voltage (I-V) characteristics of the assembled DSSCs were evaluated using a 530 W xenon lamp (XIL model 05A50KS source units). The incident photon-to-current efficiency (IPCE, PV measurements, Inc.) was measured from 300 nm to 800 nm under short-circuit conditions.

Chapter 3. Results and discussion

3.1 Fabrication and microscopic observation of the STCS-NPs

Figure 2 shows transmission electron microscopy (TEM) and field-emission scanning electron microscopy (FE-SEM) images of monodispersed spherical STCS-NPs after calcination at 600 °C. The TiO₂ coated SiO₂-NPs have a fairly uniform diameter of *ca.* 110 nm, 240 nm, 530 nm. Their diameters were controlled by varying the size of SiO₂ core template, and the TiO₂ shell thickness was precisely controlled to be same (*ca.* 10 nm). The TEM and SEM images displayed that the SiO₂ core was successfully coated with TiO₂-NPs, resulting in a rough surface morphology.

Figure 2 Transmission electron microscopy (TEM) images and field-emission scanning electron microscopy (FE-SEM) images of (a, d) STCS-NPs with diameters of *ca.* 110 nm, (b, e) STCS-NPs with diameters of *ca.* 240 nm, (c, f) STCS-NPs with diameters of *ca.* 530 nm.

Figure 3 displays SEM/energy dispersive X-ray spectroscopy (SEM/EDX) spectra. The results indicated that the atomic ratio between Si and Ti was 46:54 for 110 nm STCS (CS110) NPs, 80 : 20 for 240 nm STCS (CS240) NPs and 92 : 8 for 530 nm STCS (CS530) NPs due to different size of silica core and identical shell thickness of core/shell structure. The diameters and shell thicknesses of STCS-NPs were determined by calculating weight ratio of Si and Ti (Table 1). The diameters of each STCS-NPs were 110 nm, 240 nm, 530 nm and shell thickness was identical as 10 nm.

To determine the atomic distribution, scanning TEM/energy dispersive X-ray (STEM-EDX) line analyses were performed on STCS-NPs (Figure 4). The Ti line width was *ca.* 10~20 nm and diameters of the NPs were a) 110 nm, b) 240 nm, c) 530 nm which agrees with the TEM images.

Figure 3. SEM/Energy dispersive X-ray spectroscopy (EDX) spectra of (a) CS110, (b) CS240 and (c) CS530 NPs. The diameter of CS-NPs was 110 nm, 240 nm, 530 nm and shell thickness is identical as 10 nm after weight ratio calculation.

Table 1. SEM/EDX results of the STCS-NPs with diameters of 110 nm, 240 nm and 530 nm.

	Element	Atomic %	Weight %
CS110	Si	45.88	33.20
	Ti	54.12	66.80
CS240	Si	79.32	69.22
	Ti	20.68	30.78
CS530	Si	92.00	87.08
	Ti	8.00	12.92

Figure. 4 STEM-EDX line mapping of (a) CS110, (b) CS240 and (c) CS530 NPs.

The crystallinity of the STCS-NPs was confirmed by X-ray diffraction (XRD) patterns. Figure 5 demonstrates the XRD patterns of STCS NPs; all of the diffraction peaks were perfectly indexed to the anatase phase (JCPDS No. 21-1272). Particularly, the strong diffraction peak at $2\theta = 25.3^\circ$ (101) of the STCS-NPs corresponded well to the peak of anatase TiO_2 . It was revealed that electron transport was faster in the anatase phase of TiO_2 than the rutile phase of TiO_2 , leading to a better photovoltaic performance.[30] The broad band centered at $2\theta = 22.0^\circ$ implied the existence of an SiO_2 amorphous phase (JCPDS No. 29-0085). Judging from these data, the TiO_2 anatase phase coexisted with the SiO_2 amorphous phase in STCS-NPs.

Figure. 5 X-ray diffraction (XRD) patterns for a) CS110, b) CS240 and c) CS530 NPs.

The letter “A” denotes peaks for the anatase phase.

3.2 Optical property analysis

The scattering effect of particles is strongly dependent on their diameter and refractive index as Ferber *et al.* suggested.[11] Therefore, to investigate the effect of size and refractive index (n) on light-scattering efficiency, the optical reflectance of $\sim 10\mu\text{m}$ thick film of NPs was characterized by UV-Vis diffuse reflectance spectroscopy (DRS).

Figure 6a represents the DRS spectra of STCS-NPs with different diameters to evaluate the size dependency of the scattering effect. Comparing the STCS-NPs, the reflectance gets higher with increasing size of NPs. It was also observed that the films derived from CS240 and CS530 showed the characteristic photonic reflectance peaks at $\sim 530\text{ nm}$ and $\sim 650\text{ nm}$, respectively due to the ordering of monodisperse particles. Therefore, the photonic reflectance peaks

confirm uniform sizes of particles. Figure 6b displays the UV-Vis absorption spectra of binary mixtures composed of the STCS-NPs and nanocrystalline TiO_2 particles with dye. The absorbance of the film including CS240-NPs was higher than the film with CS530-NPs. The results indicate that smaller surface area of CS530-NPs cause lower dye loading and light absorption.

Figure 7a shows the DRS spectra of SiO_2 , TiO_2 , and STCS-NPs of identical size of 240 nm. The reflectance of anatase TiO_2 -NPs ($n_{\text{TiO}_2} = 2.49$) was higher than that of SiO_2 -NPs ($n_{\text{SiO}_2} = 1.47$); this was attributed to the increase in the scattering efficiency due to the increase in the refractive index difference between the NPs and the surrounding matrix ($n_{\text{air}} = 1.00$). Additionally, it is noteworthy that the reflectance of the STCS-NPs was comparable to that of the TiO_2 -NPs, indicating that the STCS-NPs had high light-scattering ability close to TiO_2 -NPs which was well known scattering material. Furthermore, the

Figure 6. (a) Diffused reflectance spectra (DRS) and (b) UV-Vis absorption spectra of 110 nm, 240 nm, 530 nm STCS-NPs.

Figure 7. (a) Diffuse reflectance spectra (DRS) and (b) UV-Vis absorption spectra of SiO₂-NPs, TiO₂-NPs, and STCS-NPs.

absorbance of STCS-NPs gets higher than TiO_2 -NPs after adsorbing dye and incorporating with nanocrystalline TiO_2 -NPs.

Figure 8 illustrates the light-scattering path of TiO_2 and STCS NP based on geometric optics.[40] The incident light reflected in a similar manner from the TiO_2 -NP and STCS-NP surfaces, because their surfaces consisted of TiO_2 . However, for the STCS-NPs, the light refracted in the STCS-NP and went through modified internal reflection path, due to the difference of reflective index in the core/shell structure. Figure 8a illustrates the light pathway in a TiO_2 -NP. Typically, Mie scattering occurs when the particle size is comparable to the wavelength of incident light; in this case, light is scattered from the large particle in the forward direction, as shown in Figure 8a. Figure 8b displays the modified light pathway in an STCS-NP. In the case of STCS-NPs, it is expected that light undergoes modified internal reflection and mostly emerges from the STCS-NP in

the backward direction, resulting in stronger backscattering. This suggests that the structure of the STCS-NP contributed to the increase in the scattering efficiency. In addition, the light scattering of STCS-NPs leads to optical confinement in a DSSC. Consequently, the PCE should be enhanced due to the increased probability of interaction between the photons and the dye molecules.

Figure 8. Schematic illustration for light scattering by (a) $\text{TiO}_2\text{-NP}$ and (b) STCS-NP on the basis of geometric optics.

3.3. Photovoltaic performance of DSSCs

Figure 10 represents a schematic configuration of the assembled DSSC, which is composed of STCS-NPs and nanocrystalline TiO_2 particles in the working electrode. In order to investigate the dependence of the scattering properties of LSMs on size and refractive index, CS110-NPs, CS240-NPs, CS530-NPs, SiO_2 -NPs and TiO_2 -NPs were incorporated with nanocrystalline TiO_2 particles respectively. The diameters of the SiO_2 -NPs, TiO_2 -NPs, STCS-NPs, and the film thickness of each film deposited on the fluorine-doped tin oxide (FTO) glass, were carefully controlled to be the identical.

Figure 11 displays cross-section FESEM image of STCS-NPs incorporated with nanocrystalline TiO_2 paste on the electrode. To examine the influence of the STCS-NPs on the photovoltaic properties of DSSCs, the STCS-NPs were incorporated with nanocrystalline

TiO₂ particles (TiO₂:STCS 80:20 wt/wt), which formed a 7.5-μm-thick film on FTO glass

Figure 9. Schematic configuration of a dye-sensitized solar cell (DSSC) that has SiO₂/TiO₂ core/shell nanoparticles (STCS-NPs) incorporating nanocrystalline TiO₂ particles in the working electrode.

Figure 10. Cross-section FESEM image of STCS-NPs incorporated with nanocrystalline TiO_2 paste on the electrode. (Inset: surface SEM image of the film. Black arrows indicate incorporated STCS-NPs.)

Figure 12 shows photocurrent density–voltage curves (J–V curves) for the DSSCs with different size of STCS-NPs. The photovoltaic parameters, such as the short-circuit photocurrent density (J_{sc}), open-circuit voltage (V_{oc}), fill factor (FF), and power conversion efficiency (PCE), are summarized in Table 2. By introducing the different sizes of STCS-NPs as LSMs, the solar cell device containing only TiO_2 -NPs had a J_{sc} of 12.35 mA cm⁻² and PCE of 6.49%, whereas the device with CS240-NPs had a J_{sc} of 15.91 mA cm⁻² and PCE of 7.83%, representing ca. 20% improvement over the film containing only TiO_2 -NPs. (Table 2) Interestingly, nevertheless the scattering efficiency of CS530-NPs was highest among the different sizes of STCS-NPs, PCE of ST530-NPs incorporating DSSC was lower than that of CS240 containing DSSC. This result suggests that too large diameter of CS530-NPs causes decrease of internal surface area and insufficient dye attachment.[32] Therefore, the reflectance of the cell

containing CS530-NPs might be enhanced but absorbance due to photoexcitation of the dye was not increased. In the case of J_{sc} , the increase of the J_{sc} for the STCS-NPs was measured following sequence; CS110 < CS530 < CS240. This tendency was well matched to PCE results.

Figure 13 shows the incident-photon-to-current efficiency (IPCE) spectra as a function of wavelength for the DSSCs comprised of the three different sizes of STCS-NPs and pristine DSSC. A noticeable difference on the four types of the samples was observed. Because light scattering efficiency affects to higher IPCE at longer wavelength, the increase of IPCE result at longer wavelength follows the PCE results; CS110 < CS530 < CS240. These results suggest that in the case of dye-adsorbed binary mixtures of nanocrystalline TiO_2 -NPs and light-scattering particles, the main factor of high efficiency is not

Figure 11. Photocurrent density-voltage curve (J-V curve) of a DSSC based on STCS-NPs with various diameters.

Figure 12. Incident-photon-to-current conversion efficiency (IPCE)

spectra of a DSSC based on STCS-NPs with various diameters

only scattering efficiency of light-scattering particles, but also internal surface area of the particles in the electrode.

Figure 14 shows the J–V curves as a function of different LSMs. The photovoltaic parameters are also summarized in Table 2. By incorporating STCS-NPs (240 nm) with nanocrystalline TiO₂, J_{sc} increased significantly from 12.35 mA cm⁻² (pristine) to 15.91 mA cm⁻² (STCS). The increase in J_{sc} for the STCS-NPs studied can be summarized as follows: SiO₂ < TiO₂ < STCS; the PCEs followed a similar trend. Our results showed that the DSSC with STCS-NPs had a PCE value of 7.83 %, while that using TiO₂-NPs achieved a PCE of 7.38 %. These results indicate that the PCE of the DSSC with STCS-NPs was 6 % improved than that of the device with TiO₂-NPs, due to strong backscattering from the core/shell structure. Finally, DSSCs containing STCS-NPs exhibited an enhanced PCE of 20 %, compared with the pristine DSSC containing only nanocrystalline TiO₂ particles

whose PCE value was 6.49 %. The results suggest that the optical confinement effect of scattered light from STCS-NPs improved the PCE of the cell.

Figure 15 shows the IPCE spectra as a function of wavelength for the four samples. The absolute IPCE of STCS was the highest over the entire wavelength range, which is in good agreement with the observed highest J_{sc} . In particular, the higher IPCE at longer wavelengths was attributed to better light-scattering efficiency because the LSMs could scatter the longer wavelengths and improve light absorption in this region.[21]

Figure 13 Photocurrent density–voltage curve (J–V curve) of a DSSC based on SiO₂-NPs, TiO₂-NPs, and STCS-NPs as scattering materials.

Figure 14 Incident-photon-to-current conversion efficiency (IPCE) spectra of a DSSC based on SiO₂-NPs, TiO₂-NPs, and STCS-NPs as scattering materials

Table 2 Comparison of short-circuit photocurrent density (J_{sc}), open-circuit voltage (V_{oc}), fill factor (FF), and power conversion efficiency (PCE).

	J_{sc} (mA cm ⁻²)	V_{oc} (V)	Fill factor	PCE(%)
Pristine	12.35	0.73	0.71	6.49
SiO ₂	13.17	0.72	0.72	6.84
TiO ₂	14.56	0.73	0.70	7.38
CS110	14.28	0.72	0.71	7.28
CS240	15.91	0.71	0.70	7.83
CS530	14.69	0.72	0.69	7.33

Chapter 4. Conclusion

In conclusion, we fabricated monodisperse $\text{SiO}_2/\text{TiO}_2$ core/shell nanoparticles (STCS-NPs) with diameters of 110, 240, 530 nm to investigate the effect of size and refractive index on light-scattering properties. Uniform shell thickness was *ca.* 10 nm and the crystallinity of the TiO_2 shell was revealed to anatase phase. The light scattering efficiency was increased with increasing size of NPs. But in the case of dye-adsorbed binary mixtures of nanocrystalline TiO_2 -NPs and light-scattering particles, large LSMs (*ca.* 530 nm) shows lower efficiency than 240 nm due to insufficient dye adsorption. Also, it was shown that the structure of the STCS-NPs, consisting of a low refractive index core and high refractive index shell, contributed to the high scattering efficiency. Additionally, for the same particle size and film thickness, the DSSC incorporating STCS-NPs exhibited the most

enhanced PCE, compared with that using SiO_2 and TiO_2 NPs. Accordingly, the DSSC with CS240-NPs demonstrated 20 % improved PCE than that based on nanocrystalline TiO_2 particles alone. Finally, the designed synthesis of scattering materials considering refractive indices could provide interesting new opportunities for the development of highly efficient DSSCs.

References

- [1] B. O'Regan and M. Grätzel, *Nature*, **1991**, 353, 737-740.
- [2] M. Grätzel, *Nature*, **2001**, 414, 338-344.
- [3] A. Yella, H. W. Lee, H. N. Tsao, C. Yi, A. K. Chandiran, M. K. Nazeeruddin, E. W. G. Diau, C. Y. Yeh, S. M. Zakeeruddin and M. Grätzel, *Science*, **2011**, 334, 629-634.
- [4] M. Grätzel, *Journal of Photochemistry and Photobiology C: Photochemistry Reviews*, **2003**, 4, 145-153.
- [5] A. Hagfeldt, G. Boschloo, L. Sun, L. Kloo and H. Pettersson, *Chemical Reviews*, **2010**, 110, 6595-6663.
- [6] S. Cho, S. H. Hwang, C. Kim and J. Jang, *Journal of Materials Chemistry*, **2012**, 22, 12164-12171.
- [7] S. Agarwala, M. Kevin, A. S. W. Wong, C. K. N. Peh, V. Thavasi and G. W. Ho, *ACS Applied Materials and Interfaces*, **2010**, 2, 1844-1850.

- [8] D. Chen, F. Huang, Y. B. Cheng and R. A. Caruso, *Advanced Materials*, **2009**, 21, 2206-2210.
- [9] K. Hara, M. Kurashige, Y. Dan-Oh, C. Kasada, A. Shinpo, S. Suga, K. Sayama and H. Arakawa, *New Journal of Chemistry*, **2003**, 27, 783-785.
- [10] N. Robertson, *Angewandte Chemie - International Edition*, **2006**, 45, 2338-2345.
- [11] Q. Zhang, C. S. Dandeneau, X. Zhou and C. Cao, *Advanced Materials*, **2009**, 21, 4087-4108.
- [12] A. Usami, *Solar Energy Materials and Solar Cells*, **2000**, 64, 73-83.
- [13] I. G. Yu, Y. J. Kim, H. J. Kim, C. Lee and W. I. Lee, *Journal of Materials Chemistry*, **2011**, 21, 532-538.
- [14] F. Huang, D. Chen, X. L. Zhang, R. A. Caruso and Y. B. Cheng, *Advanced Functional Materials*, **2010**, 20, 1301-1305.
- [15] L. Yang and W. W. F. Leung, *Advanced Materials*, **2011**, 23, 4559-4562.
- [16] B. Tan and Y. Wu, *Journal of Physical Chemistry B*, **2006**, 110, 15932-

15938.

[17] K. Yu and J. Chen, *Nanoscale Research Letters*, **2009**, 4, 1-10.

[18] H. J. Koo, Y. J. Kim, Y. H. Lee, W. I. Lee, K. Kim and N. G. Park,
Advanced Materials, **2008**, 20, 195-199.

[19] J. Ferber and J. Luther, *Solar Energy Materials and Solar Cells*, **1998**, 54,
265-275.

[20] Z. -S. Wang, H. Kawauchi, T. Kashima, H. Arakawa, *Coord. Chem. Rev.*
2004, 248, 1381

[21] R. K. Iler, *The chemistry of Silica*, Plenum Press, **1979**

[22] D. Zhao, J. Feng, Q. Huo, N. Meloxh, G. H. Fredrickson, B. F. Chmelka,
G. D. Stucky, *Science*, **1998**, 279, 548

[23] B. G. Trewyn, I. I. Slowing, S. Giri, H. -T. Chen, V. S. -Y. Lin, *Acc.*
Chem. Res. **1997**, 40, 846

[24] D. S. Shephard, T. Maschmeyer, B. F. G. Johnson, J. M. Thomas, G.
Sankar, D. Ozkaya, W. Zhou, R. D. Oldroyd, R. G. Bell, *Angew. Chem.*

- Int. Ed. Engi, **1997**, 36, 2242
- [25] I. I. Slowing, B. G. Trewyn, S. Giri, V. S. –Y. Lin, Adv. Func. Mater.,
2007, 17, 1225
- [26] C. Anderson, AJ, Bard, Journal of physical chemistry B, **1997**, 14, 2611
- [27] D. Hanaor, C. Sorrell, J. Mater. Sci., **2011**, 46, 855
- [28] Md. K. Nazeeruddin, R. Humphry-Baker, P. Liska, M. Gratzel, J. Phys.
CHem. B, **2003**, 107, 8981
- [29] I. Robel, V. Subramanian, M. Kuno, P. V. Kamat, Jpn, J. Am. Chem. Soc.,
2006, 128, 2385
- [30] K. Shankar, G. K. Mor, H. E. Prakasam, O. K. Varghese, C. A. Grimes,
Langmuir, **2007**, 23, 12445
- [31] A. L. Aden and M. Kerker, Journal of Applied Physics, **1951**, 22, 1242-
1246.
- [32] Y. L. Geng, C. W. Qiu and S. Zouhdi, Journal of Applied Physics, **2008**,
104.

- [33] R. W. Johnson, E. S. Thiele and R. H. French, Tappi journal, **1997**, 80, 233-239.
- [34] W. P. Hsu, R. Yu and E. Matijević, Journal of Colloid and Interface Science, **1993**, 156, 56-65.
- [35] A. Small, S. Hong and D. Pine, Journal of Polymer Science, Part B: Polymer Physics, **2005**, 43, 3534-3548.
- [36] H. Xu, X. Chen, S. Ouyang, T. Kako and J. Ye, Journal of Physical Chemistry C, **2012**, 116, 3833-3839.
- [37] R. Watanabe, T. Yokoi, E. Kobayashi, Y. Otsuka, A. Shimojima, T. Okubo and T. Tatsumi, Journal of Colloid and Interface Science, **2011**, 360, 1-7.
- [38] M. Choi, C. Kim, S. Ok Jeon, K. Soo Yook, J. Yeob Lee and J. Jang, Chemical Communications, **2011**, 47, 7092-7094.
- [39] N. G. Park, J. Van De Lagemaat and A. J. Frank, Journal of Physical Chemistry B, **2000**, 104, 8989-8994.
- [40] Y. Takano and K. N. Liou, Applied Optics, **2010**, 49, 3990-3996.

초 록

SiO₂/TiO₂ 코어/셸 나노입자를 110, 240, 530 nm 크기로 정밀하게 제조하였고, 이를 이용하여 입자의 크기와 굴절률이 빛 산란 효과에 미치는 영향을 연구하였다. 입자의 크기에 따른 SiO₂/TiO₂ 코어/셸 나노입자의 광학적 특성을 고찰하였으며, 동일한 크기의 SiO₂, TiO₂ 나노입자와 비교하였다. 그 결과 입자의 크기가 110, 240, 530 nm 로 커질수록 산란 효과가 증가하는 것을 확인하였을 뿐만 아니라 굴절률이 낮은 SiO₂ 코어와 굴절률이 높은 TiO₂ 셸로 이루어진 코어/셸 구조가 높은 산란 효과를 유도하는 것을 관찰하였다. 이러한 SiO₂/TiO₂ 코어/셸 나노입자를 염료감응태양전지의 산란 물질로 적용한 결과, 240 nm 크기의 코어/셸을 포함하는 전지의 효율이 (7.83 %) 20~30 nm 크기의 TiO₂ 나노입자로만 이루어진 전지의 효율 (6.49 %) 보다 약 20 % 향상된 결과를 얻을 수 있었다.

주요어: 염료감응태양전지, 빛 산란 물질, 코어/셸 나노입자

학번: 2011-22919